

# Alamos

## BASIC INFORMATION

Launch Date	01/09/2013	Tariff item number	54079300
Delivery time special lab dip	4	Number of colour ways	9
Country of origin	India	Characteristics	Jacquard
Vertical repeat (cm)	3.80	Vertical repeat (inch)	1.50
Horizontal repeat (cm)	4.50	Horizontal repeat (inch)	1.77
Roll diameter (in cm, for 50 meters)	0.00	Roll diameter (in inch, for 50 meter)	0.00
Face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	40	MID	INDICDEC751MUM
MID id	INDICDEC751MUM		

## CATEGORY

Colouring type	Yarn dyed	Type of print/dye - disperse	Yes
Type of print/dye - reactive	Yes	Type of finish	airo
After treatment - none	Yes		

### Care codes



### Use codes

Use code - curtains/draperies	Yes	Use code - upholstery	Yes
Use code - bed covering	Yes	Use code - accessories	Yes

## FABRIC TYPE

Composition	74% Polyester, 26% Viscose	Average yarn number	27.48
Weaving type - jacquard	Yes	Construction	66.14x21.24
Embroidery width (cm)	0.00	Embroidery Width (Inch)	0.00
Useable width (cm)	143.00	Useable width (inch)	56.30
Full width (cm)	145.00	Full width (inch)	57.09
Woven	Yes	Weight (g/m <sup>2</sup> )	318

## FR STANDARDS

BS5852 source 0	Yes	BS5852 source 1 comment	Yes, with FR coating
CAL 117 (Complies)	Yes	FMVSS 302 (Pass)	Yes
NFPA 260	Yes		

## ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

## SPECIFICATIONS

Martindale (rubs)	20,000	Colour fastness to light	6
Pilling	4	Wyzenbeek (double rubs)	30,000
Wyzenbeek wire screen (double rubs - residential use, stopped after 15 000 double rubs)	15,000	Wyzenbeek cotton duck type general upholstery	Yes

### Colour fastness to light - ISO 105-B02

Colour fastness to light	6
--------------------------	---

### Colour fastness to water - ISO 105-E01

Colour fastness to water	5
--------------------------	---

### Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	4
-------------------------	---

### Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	3-4
-------------------------	-----

### Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4-5
-------------------------	-----

### Tearing strength - ISO 13937-3

Tearing strength warp (N)	160	Tearing strength weft (N)	230
---------------------------	-----	---------------------------	-----

### Tensile strength - ISO 13934-1

Tensile strength warp (N/5cm)	1900	Tensile strength weft (N/5cm)	960
-------------------------------	------	-------------------------------	-----

### Elongation - ISO 13934-1

Elongation warp (%)	42	Elongation weft (%)	27
---------------------	----	---------------------	----

**Seam slippage - ISO 13936-2**

Seam slippage warp (mm)	4	Seam slippage weft (mm)	5
-------------------------	---	-------------------------	---

**Resistance to domestic washing 30°C (indicated in %) - ISO 6330**

Dimensional change warp	0.73-	Dimensional change warp after ironing	0.60-
Dimensional change weft	0.57-	Dimensional change weft after ironing	0.47-
Colour fastness (ISO 105 C06)	4-5		

**Resistance to domestic washing 60°C (indicated in %) - ISO 6330**

Dimensional change warp	0.70-	Dimensional change warp after ironing	0.60-
Dimensional change weft	0.60-	Dimensional change weft after ironing	0.60-
Colour fastness (ISO 105 C06)	5		

**Resistance to dry cleaning P (indicated in %) - ISO 105 D01**

Dimensional change warp	0.57-	Dimensional change warp after ironing	0.53-
Dimensional change weft	0.27-	Dimensional change weft after ironing	0.33-
Colour fastness (ISO 105 D01)	4-5		

**Dimensional stability (indicated in %) - ISO 3759**

Dimensional change warp	0.05-	Dimensional change warp after ironing without steam	0.00
Dimensional change warp after ironing with steam	0.33-	Dimensional change weft	0.08-
Dimensional change weft after ironing without steam	0.00	Dimensional change weft after ironing with steam	0.00

**CONSTRUCTION**

**Yarn 1**

Warp composition	100% Polyester	Warp yarn sizes	155/34/450
Warp threads per cm	66.14	Warp turns per meter (TPM)	NA
Warp type man made	Yes	Warp type filament	Yes
Warp specification textured	Yes		

**Yarn 2**

Weft composition	100% Polyester	Weft yarn sizes	1000 d
Weft threads per cm	7.08	Weft turns per meter (TPM)	NA

Weft type man made	Yes	Weft type filament	Yes
Weft specification textured	Yes		

**Yarn 3**

Weft composition	100% Viscose	Weft yarn sizes	1/6 (5.5)
Weft threads per cm	7.08	Weft turns per meter (TPM)	NA
Weft type natural	Yes	Weft type staple	Yes
Weft specification not textured	Yes		

**Yarn 4**

Weft composition	100% Polyester	Weft yarn sizes	300 d
Weft threads per cm	7.08	Weft turns per meter (TPM)	NA
Weft type natural	Yes	Weft type staple	Yes
Weft specification textured	Yes		