

Kara

BASIC INFORMATION

| | | | |
|--------------------------------------|----------------|---------------------------------------|----------------|
| Launch Date | 01/09/2015 | Tariff item number | 58013700 |
| Delivery time special lab dip | 2 | Number of colour ways | 6 |
| Country of origin | India | Characteristics | Velvet |
| Vertical repeat (cm) | 7.80 | Vertical repeat (inch) | 3.07 |
| Horizontal repeat (cm) | 8.80 | Horizontal repeat (inch) | 3.46 |
| Roll diameter (in cm, for 50 meters) | 0.00 | Roll diameter (in inch, for 50 meter) | 0.00 |
| Face in | Yes | Minimum for special colour (m) | 1000 |
| Average piece length (m) | 35 | MID | INDICDEC751MUM |
| MID id | INDICDEC751MUM | | |

CATEGORY

| | | | |
|----------------|------------|------------------------------|-----|
| Colouring type | Piece dyed | Type of print/dye - reactive | Yes |
| Type of finish | stenter | After treatment - none | Yes |

Care codes

Care code - comments iron on reverse side



Use codes

| | | | |
|-------------------------------|-----|------------------------|-----|
| Use code - curtains/draperies | Yes | Use code - upholstery | Yes |
| Use code - bed covering | Yes | Use code - accessories | Yes |

FABRIC TYPE

| | | | |
|-------------------------|--|----------------------------|-----------|
| Composition | 45% Viscose, 35% Cotton, 20% Polyester | Average yarn number | 7.01 |
| Weaving type - jacquard | Yes | Construction | 8.94x5.49 |
| Embroidery width (cm) | 0.00 | Embroidery Width (Inch) | 0.00 |
| Useable width (cm) | 143.00 | Useable width (inch) | 56.30 |
| Full width (cm) | 145.00 | Full width (inch) | 57.09 |
| Woven | Yes | Weight (g/m ²) | 492 |

FR STANDARDS

| | | | |
|------------------|-----|--------------------|-----|
| BS5852 source 0 | Yes | CAL 117 (Complies) | Yes |
| FMVSS 302 (Pass) | Yes | NFPA 260 | Yes |

ENVIRONMENTAL STANDARDS

| | | | |
|----------|-----|-----------|-----|
| Oeko-Tex | Yes | ISO 14001 | Yes |
|----------|-----|-----------|-----|

SPECIFICATIONS

| | | | |
|---|---------|---|--------|
| Martindale (rubs) | 100,000 | Colour fastness to light | 4-5 |
| Pilling | 4-5 | Wyzenbeek (double rubs) | 40,000 |
| Wyzenbeek wire screen (double rubs - residential use, stopped after 15 000 double rubs) | 15,000 | Wyzenbeek cotton duck type heavy upholstery | Yes |

Colour fastness to light - ISO 105-B02

| | |
|--------------------------|-----|
| Colour fastness to light | 4-5 |
|--------------------------|-----|

Colour fastness to water - ISO 105-E01

| | |
|--------------------------|---|
| Colour fastness to water | 5 |
|--------------------------|---|

Colour fastness to dry rub - ISO 105-X12

| | |
|-------------------------|-----|
| Colour fastness dry rub | 4-5 |
|-------------------------|-----|

Colour fastness to wet rub - ISO 105-X12

| | |
|-------------------------|-----|
| Colour fastness wet rub | 3-4 |
|-------------------------|-----|

Colour fastness to wear - ISO 12947-2

| | |
|-------------------------|---|
| Colour fastness to wear | 4 |
|-------------------------|---|

Tearing strength - ISO 13937-3

| | | | |
|---------------------------|----|---------------------------|----|
| Tearing strength warp (N) | 20 | Tearing strength weft (N) | 51 |
|---------------------------|----|---------------------------|----|

Tensile strength - ISO 13934-1

| | | | |
|-------------------------------|------|-------------------------------|-----|
| Tensile strength warp (N/5cm) | 1600 | Tensile strength weft (N/5cm) | 790 |
|-------------------------------|------|-------------------------------|-----|

Elongation - ISO 13934-1

| | | | |
|---------------------|----|---------------------|----|
| Elongation warp (%) | 29 | Elongation weft (%) | 10 |
|---------------------|----|---------------------|----|

Seam slippage - ISO 13936-2

| | | | |
|-------------------------|---|-------------------------|---|
| Seam slippage warp (mm) | 3 | Seam slippage weft (mm) | 3 |
|-------------------------|---|-------------------------|---|

Resistance to domestic washing 30°C (indicated in %) - ISO 6330

| | | | |
|-------------------------------|-------|---------------------------------------|-------|
| Dimensional change warp | 2.51- | Dimensional change warp after ironing | 2.32- |
| Dimensional change weft | 1.95- | Dimensional change weft after ironing | 1.92- |
| Colour fastness (ISO 105 C06) | 5 | | |

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

| | | | |
|-------------------------------|-------|---------------------------------------|-------|
| Dimensional change warp | 3.87- | Dimensional change warp after ironing | 3.81- |
| Dimensional change weft | 2.61- | Dimensional change weft after ironing | 2.52- |
| Colour fastness (ISO 105 C06) | 4-5 | | |

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

| | | | |
|-------------------------------|-------|---------------------------------------|-------|
| Dimensional change warp | 1.29- | Dimensional change warp after ironing | 0.99- |
| Dimensional change weft | 0.70- | Dimensional change weft after ironing | 0.53- |
| Colour fastness (ISO 105 D01) | 4-5 | | |

Dimensional stability (indicated in %) - ISO 3759

| | | | |
|---|-------|---|------|
| Dimensional change warp | 0.17 | Dimensional change warp after ironing without steam | 0.07 |
| Dimensional change warp after ironing with steam | 0.20- | Dimensional change weft | 0.08 |
| Dimensional change weft after ironing without steam | 0.07 | Dimensional change weft after ironing with steam | 0.00 |

CONSTRUCTION

Yarn 1

| | | | |
|---------------------------|-------------|---------------------------------|--------|
| Warp composition | 100% Cotton | Warp yarn sizes | 2/30's |
| Warp threads per cm | 8.94 | Warp turns per meter (TPM) | NA |
| Warp type natural | Yes | Warp type staple | Yes |
| Warp specification combed | Yes | Warp specification not textured | Yes |

Yarn 2

| | | | |
|---------------------|--------------------|----------------------------|--------|
| Weft composition | Pile: 100% Viscose | Weft yarn sizes | 2/24's |
| Weft threads per cm | 11.02 | Weft turns per meter (TPM) | NA |



| | | | |
|---------------------------------|-----|------------------|-----|
| Weft type natural | Yes | Weft type staple | Yes |
| Weft specification not textured | Yes | | |

Yarn 3

| | | | |
|---------------------------------|--------------------|----------------------------|---------|
| Weft composition | Pile: 100% Viscose | Weft yarn sizes | 450 den |
| Weft threads per cm | 9.03 | Weft turns per meter (TPM) | NA |
| Weft type natural | Yes | Weft type staple | Yes |
| Weft type filament | Yes | | |
| Weft specification not textured | Yes | | |

Yarn 4

| | | | |
|---------------------------|-------------|---------------------------------|--------|
| Weft composition | 100% Cotton | Weft yarn sizes | 2/30's |
| Weft threads per cm | 5.49 | Weft turns per meter (TPM) | NA |
| Weft type natural | Yes | Weft type staple | Yes |
| Weft specification combed | Yes | Weft specification not textured | Yes |