

Lungo

BASIC INFORMATION

Launch Date	01/01/2018	Tariff item number	54075300
Delivery time special lab dip	4	Number of colour ways	4
Country of origin	Turkey	Characteristics	Texture
Vertical repeat (cm)	plain	Vertical repeat (inch)	plain
Horizontal repeat (cm)	plain	Horizontal repeat (inch)	plain
Roll diameter (in cm, for 50 meters)	0.00	Roll diameter (in inch, for 50 meter)	0.00
Face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	50	MID	TRTEXTRABUR
MID id	TRTEXTRABUR		

CATEGORY

Colouring type	Yarn dyed	Treatment	Calender
After treatment - other specification	FibreGuard		

Care codes



Use codes

Use code - upholstery	Yes	Use code - bed covering	Yes
Use code - accessories	Yes		

FABRIC TYPE

Composition	100% Polyester	Average yarn number	15.99
Weaving type - dobby	Yes	Construction	33x26
Embroidery width (cm)	0.00	Embroidery Width (Inch)	0.00
Useable width (cm)	140.00	Useable width (inch)	55.12
Full width (cm)	142.00	Full width (inch)	55.91
Woven	Yes	Weight (g/m ²)	369

FR STANDARDS

BS5852 source 0	Yes	BS5852 source 1 comment	Yes, with FR coating
CAL 117 (Complies)	Yes	CAN/ULC-S109 Large flame test	Yes
CAN/ULC-S109 Small flame test	Yes	FMVSS 302 (Pass)	Yes
NFPA 260	Yes	NFPA 701	Yes

ENVIRONMENTAL STANDARDS

Oeko-Tex	Yes	ISO 14001	Yes
----------	-----	-----------	-----

SPECIFICATIONS

Martindale (rubs)	100,000	Colour fastness to light	4
Pilling	4-5	Brush pilling	4-5
Wyzenbeek (double rubs)	200,000	Wyzenbeek wire screen (double rubs - residential use, stopped after 15 000 double rubs)	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light	4
--------------------------	---

Colour fastness to water - ISO 105-E01

Colour fastness to water	4
--------------------------	---

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub	3-4
-------------------------	-----

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub	3-4
-------------------------	-----

Colour fastness to wear - ISO 12947-2

Colour fastness to wear	4-5
-------------------------	-----

Tearing strength - ISO 13937-3

Tearing strenth warp (N)	500	Tearing strength weft (N)	750
--------------------------	-----	---------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp (N/5cm)	2000	Tensile strength weft (N/5cm)	1800
-------------------------------	------	-------------------------------	------

Elongation - ISO 13934-1

Elongation warp (%)	21.5	Elongation weft (%)	26.5
---------------------	------	---------------------	------

Seam slippage - ISO 13936-2

Seam slippage warp (mm)	5	Seam slippage weft (mm)	5
-------------------------	---	-------------------------	---

Resistance to domestic washing 30°C (indicated in %) - ISO 6330

Dimensional change warp	0.27-	Dimensional change warp after ironing	0.27-
Dimensional change weft	0.36-	Dimensional change weft after ironing	0.40-
Colour fastness (ISO 105 C06)	4		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	1.26-	Dimensional change warp after ironing	1.19-
Dimensional change weft	1.13-	Dimensional change weft after ironing	0.99-
Colour fastness (ISO 105 C06)	4		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	0.70-	Dimensional change warp after ironing	0.60-
Dimensional change weft	0.76-	Dimensional change weft after ironing	0.66-
Colour fastness (ISO 105 D01)	4		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.02	Dimensional change warp after ironing without steam	0.00
Dimensional change warp after ironing with steam	0.20-	Dimensional change weft	0.00
Dimensional change weft after ironing without steam	0.07	Dimensional change weft after ironing with steam	0.13

CONSTRUCTION

Yarn 1

Warp composition	100% Polyester	Warp yarn sizes	150 den
Warp threads per cm	24.75	Warp turns per meter (TPM)	NA
Warp type filament	Yes		
Warp specification textured	Yes		

Yarn 2

Warp composition	100% Polyester	Warp yarn sizes	1419 den
Warp threads per cm	8.25	Warp turns per meter (TPM)	NA
Warp type filament	Yes		
Warp specification not textured	Yes		

Yarn 3

Weft composition	100% Polyester	Weft yarn sizes	75 den
Weft threads per cm	19.50	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification textured	Yes		

Yarn 4

Weft composition	100% Polyester	Weft yarn sizes	1931 den
Weft threads per cm	3.25	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification not textured	Yes		

Yarn 5

Weft composition	100% Polyester	Weft yarn sizes	1419 den
Weft threads per cm	3.25	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification not textured	Yes		