

Panama

BASIC INFORMATION

Launch Date	01/03/2013	Tariff item number	54077300
Delivery time special lab dip	4	Number of colour ways	5
Country of origin	Turkey	Characteristics	Jacquard
Vertical repeat (cm)	plain	Vertical repeat (inch)	plain
Horizontal repeat (cm)	plain	Horizontal repeat (inch)	plain
Roll diameter (in cm, for 50 meters)	24.50	Roll diameter (in inch, for 50 meter)	9.60
Face in	Yes	Minimum for special colour (m)	1000
Average piece length (m)	50	MID	TRKET40IST
MID id	TRKET40IST		

CATEGORY

Colouring type	Yarn dyed	Type of print/dye - disperse	Yes
Type of finish	back coating	After treatment - none	Yes

Care codes

Care code - dry clean P Do not dry-clean

			
---	---	---	---

Use codes

Use code - upholstery	Yes	Use code - bed covering	Yes
Use code - accessories	Yes		

FABRIC TYPE

Composition	100% Polypropylene	Average yarn number	4.91
Weaving type - jacquard	Yes	Construction	7.1x6
Embroidery width (cm)	0.00	Embroidery Width (Inch)	0.00
Useable width (cm)	138.00	Useable width (inch)	54.30
Full width (cm)	140.00	Full width (inch)	55.10
Woven	Yes	Weight (g/m ²)	267

FR STANDARDS

BS5852 source 0	Yes	BS5852 source 1 comment	Yes, with FR coating
CAL 117 (Complies)	Yes	NFPA 260	Yes

ENVIRONMENTAL STANDARDS

Oeko-Tex Yes

SPECIFICATIONS

Martindale (rubs)	25,000	Colour fastness to light	6
Pilling	4	Brush pilling	4-5
Wyzenbeek (double rubs)	30,000	Wyzenbeek wire screen (double rubs - residential use, stopped after 15 000 double rubs)	15,000
Wyzenbeek cotton duck type general upholstery	Yes		

Colour fastness to light - ISO 105-B02

Colour fastness to light 6

Colour fastness to water - ISO 105-E01

Colour fastness to water 5

Colour fastness to dry rub - ISO 105-X12

Colour fastness dry rub 4-5

Colour fastness to wet rub - ISO 105-X12

Colour fastness wet rub 4-5

Colour fastness to wear - ISO 12947-2

Colour fastness to wear 4

Tearing strength - ISO 13937-3

Tearing strength warp (N)	150	Tearing strength weft (N)	140
---------------------------	-----	---------------------------	-----

Tensile strength - ISO 13934-1

Tensile strength warp (N/5cm)	1100	Tensile strength weft (N/5cm)	930
-------------------------------	------	-------------------------------	-----

Elongation - ISO 13934-1

Elongation warp (%)	36	Elongation weft (%)	38
---------------------	----	---------------------	----

Seam slippage - ISO 13936-2

Seam slippage warp (mm)	4	Seam slippage weft (mm)	4
-------------------------	---	-------------------------	---

Resistance to domestic washing 30°C (indicated in %) - ISO 6330

Dimensional change warp	1.52-	Dimensional change warp after ironing	1.25-
Dimensional change weft	1.25-	Dimensional change weft after ironing	0.79-
Colour fastness (ISO 105 C06)	4-5		

Resistance to domestic washing 60°C (indicated in %) - ISO 6330

Dimensional change warp	4.69-	Dimensional change warp after ironing	4.43-
Dimensional change weft	1.95-	Dimensional change weft after ironing	1.98-
Colour fastness (ISO 105 C06)	4-5		

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	14.51-	Dimensional change warp after ironing	14.08-
Dimensional change weft	8.26-	Dimensional change weft after ironing	8.19-
Colour fastness (ISO 105 D01)	4		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	0.21-	Dimensional change warp after ironing without steam	0.13
Dimensional change warp after ironing with steam	0.07	Dimensional change weft	0.42-
Dimensional change weft after ironing without steam	0.40	Dimensional change weft after ironing with steam	0.27-

CONSTRUCTION

Yarn 1

Warp composition	100% Polypropylene	Warp yarn sizes	1300 den
Warp threads per cm	7.10	Warp turns per meter (TPM)	NA
Warp type filament	Yes		
Warp specification textured	Yes		

Yarn 2

Weft composition	100% Polypropylene	Weft yarn sizes	1300 den
------------------	--------------------	-----------------	----------

Technical Product Summary



Weft threads per cm	6.00	Weft turns per meter (TPM)	NA
Weft type filament	Yes		
Weft specification textured	Yes		